

# Kramer Industries, Inc.

140 Ethel Road West  
Unit U  
Piscataway, NJ 08854

phone: 888-515-9443  
fax: 732-650-0556  
www.KramerIndustriesOnline.com

**“Right From The Start”**

---

## Silicon Carbide Grit #20 Mesh

### Typical Physical Properties

<b>Color</b>	Black
<b>Grain Shape</b>	Angular
<b>Magnetic Content</b>	0.2 – 0.5 %
<b>Hardness</b>	9.5 Mohs
<b>Specific Gravity</b>	3.2
<b>Bulk Density</b>	96 lbs / ft <sup>3</sup>

### Proximate Chemical Analysis

<b>SiC</b>	98.81 %	<b>Fe</b>	0.03 %
<b>C</b>	0.16 %	<b>Al</b>	0.03 %
<b>Si</b>	0.39 %	<b>CaO</b>	0.01 %
<b>SiO<sub>2</sub></b>	0.48 %	<b>MgO</b>	0.02 %

### Particle Size Distribution

Screen Size	Size Grading Specification <sup>1</sup>		% Retention <sup>2</sup>
	Lower Limit	Upper Limit	
<b>12</b>	0.0 %	0.0 %	0.0 %
<b>16</b>	0.0 %	20.0 %	15.35 %
<b>18</b>	45.0 %	100%	51.65 %
<b>25</b>	0.0 %	100%	4.95 %
<b>-25</b>	0.0 %	3.0 %	0.30 %
<b>20 (CONTROL<sup>3</sup>)</b>	70.0 %	100 %	79.40 %

**Notes:**

Testing Method: FEPA Standards: 45-1986 and 42-1984

<sup>1</sup> Specification for percentage retained on each screen size for given grade of product.

<sup>2</sup> Results of a recent batch.

<sup>3</sup> Control screen for quick confirmation of product grade.